

SPLASHMASTER COVERALL

DISPOSABLE CHEMICAL PROTECTIVE WORKWEAR




RESPIREX™


Description

Lightweight, **Type 3** liquid-tight, limited re-use hooded coverall, designed for use with a full face mask and filter or appropriate facial and respiratory protection. Manufactured from **Chemprotex™ 300** the suit is highly chemically resistant and features a comfortable spun-bonded lining inside.


Applications



Petro-Chemical



Chemical Industry



Industrial Cleaning



Chemical Transport



Nuclear



Shipping



Certification



TYPE 3 | EN14605:2005+A1 2009
Liquid-Tight Chemical Protective Clothing



TYPE 4 | EN14605:2005+A1 2009
Spray-Tight Chemical Protective Clothing



TYPE 5 | EN13982-1:2004+A1:2010
Particulate Protective Clothing



TYPE 6 | EN13034:2005+A1 2009
Limited Spray-Tight Chemical Protective Clothing



EN 14126:2018
Protective Clothing Against Infective Agents



EN 1149-5:2018
Antistatic Protective Clothing



CLASS 1 | EN 1073-2:2002
Radioactive Particulate Protective Clothing


Product Documentation



The CE Certificate, Declaration of Conformity and user instructions can all be downloaded from the product page on the Respirex website, links are in the downloads tab.

Key Features

Integral hood with **elastic face seal** for a comfortable fit around a full or half mask respirator



Adjustable **throat flap** for improved seal around the base of the facemask

Nylon **zip fitted at the front** with **double external zip flaps** with hook and loop fastening

Elasticated wrists with thumb loop

Protection against liquid chemicals (**Type 3**), infective agents and chemical warfare agents.

[Respirex recommend taping around the facemask, at the wrists and ankles]

Ten year shelf-life

Elasticated ankles

For use with customers own chemical safety boots

Accessories




HAZMAX™ Boots

A chemically-protective anti-static safety boot with an integral steel toe cap and mid sole, vulcanized rubber sole for superior slip resistance and kick off lug for hands free removal.

Sizing Chart

| Size | Chest (cm) | Height (cm) |
|----------|------------|-------------|
| Small | 88-96 | 164-170 |
| Medium | 96-104 | 170-176 |
| Large | 104-112 | 176-182 |
| X-Large | 112-124 | 182-188 |
| XX-Large | 124-136 | 188-194 |



Specifications

Splashmaster Suit

| | |
|---------------------------|-----------------|
| Pack Size (max) | 4 x 58 x 36 cm |
| Pack Weight (max) | 0.85 kg |
| Carton Qty | 20 |
| Outer Carton Size | 84 x 62 x 40 cm |
| Outer Carton Weight (max) | 19 kg |
| Commodity Code | 39262000 |

Specifications are based on an XL sized suit without optional accessories and are for guidance only

Material Properties

| Property | Test Method | Property value of Chemprotex™ 300 | Class |
|--|---|---|-------|
| Abrasion Resistance | EN ISO 12947-2:2016 | 2,000 cycles | 6 |
| Flex Cracking Resistance (visual assessment) | EN ISO 7854:1997 Method B | 1,000 cycles - Pass 2,500 cycles - Fail | 1 |
| Puncture Resistance | EN 863:1995 | 13.6 Newtons | 2 |
| Trapezoidal Tear Resistance | EN ISO 9073-4:1997 | Length 76.3 Newtons, Width 53.1 Newtons | 3 |
| Tensile strength | EN ISO 13934-1:2013 | Length 159.1 Newtons, Width 92.5 Newtons | 2 |
| Resistance to ignition | EN 13274-4:2001 Method 3 (single burner test) | No part ignited or continued to burn on removal from the flame | Pass |
| Resistance to blocking | EN 25978:1993 | No blocking | 2 |
| Seam Strength | EN ISO 13935-2:2014 | > 125 Newtons | 4 |
| Surface resistance** | EN 1149-1:2006 | Face <3.6 x 10 ⁸ Ω, Reverse <3.4 x 10 ⁷ Ω | - |

* Chemprotex™ 300 meets the resistance to ignition requirements of EN14325:2004 but is not flame resistant. PPE manufactured from Chemprotex™ 300 should not be worn in potentially flammable or explosive environments.

** Anti-static properties are not claimed for all PPE manufactured from Chemprotex™ 300. Please refer to the specific user instructions supplied with each product for detailed performance information. Regardless of the anti-static properties of any suit materials, it is the responsibility of the end-user to ensure that their working practices (e.g. grounding) achieve dissipation of any static charges which may build up on the suit during use.

Resistance to Penetration by Infective Agents

The material has passed the requirements of EN14126:2003 for protective clothing against infective agents. It is therefore suitable to provide protection against blood, blood-borne pathogens, body fluids, biologically contaminated aerosols and both wet and dry microbial penetration.

| Requirement | Test Method | Level of Performance | EN14126:2003 Class |
|---|--------------------|----------------------|--------------------|
| Resistance to wet microbial penetration | ISO 22610:2006 | > 75 min | 6 |
| Resistance to penetration by blood and body fluids using synthetic blood | ISO 16603:2004 | Pass | N/A |
| Resistance to penetration by blood-borne pathogens using bacteriophage Phi-X174 | ISO 16604:2004 | 20 kPa | 6 |
| Resistance to penetration by biologically contaminated aerosols | ISO/DIS 22611:2003 | Log > 5 | 3 |
| Resistance to dry microbial penetration | ISO 22612:2005 | <1 Log cfu | 3 |

Chemical Warfare Agent Protection

| Agent | Breakthrough time (hours) | Temperature (°C) |
|--------------------|---------------------------|------------------|
| Mustard agent (HD) | >48 | 37 |
| Sarin (GB) | >48 | 37 |
| Soman (GD) | >48 | 37 |
| VX | >48 | 37 |

The Chemprotex™ 300 material has been tested for resistance to permeation by chemical warfare agents in accordance with FINABEL O.7.C methods at the respected TNO laboratories. Both the material and seams were found to offer an extremely high level of protection against the following agents:

Chemical Permeation & Permasure®



The Splashmaster coverall is compatible with the **Permasure** toxicity modelling app, available for Android and IOS devices. Permasure calculates safe working times for a database of over 4,000 common industrial and toxic chemicals, basing its calculations of the actual working conditions at the time. For full details visit www.respirex.com/permasure

All chemical permeation tests are carried out under laboratory conditions by independent accredited laboratories in accordance with EN 374-3 unless otherwise stated.

| Chemical Name | State | CAS Number | Actual (min.) | ASTM (min.) | EN374-3 (min.) | EN Class | SSPR µg/(min.cm²) | MDPR µg/(min.cm²) | Observation |
|---|-------|------------|---------------|-------------|----------------|----------|-------------------|-------------------|-------------------|
| acetaldehyde | L | 75-07-0 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| acetic acid (30%) | L | 64-19-7 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| acetic acid (glacial) | L | 64-19-7 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| acetic anhydride | L | 108-24-7 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| acetone | L | 67-64-1 | >480 | >480 | >480 | 6 | <0.02 | 0.02 | No degradation |
| acetonitrile | L | 64047 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| acetophenone | L | 98-86-2 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| acrylamide (50%) | L | 65532 | >480 | >480 | >480 | 6 | <0.10 | 0.10 | No degradation |
| acrylic acid | L | 65660 | >480 | >480 | >480 | 6 | <0.005 | 0.005 | Discolouration |
| acrylonitrile | L | 107-13-1 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| allyl alcohol | L | 107-18-6 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| ammonia | G | 7664-41-7 | 32 | 49 | >480 | 6 | 0.17 | 0.005 | No degradation |
| ammonium hydroxide (35% NH ₃ in water) | L | 1336-21-6 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| amyl acetate-n | L | 628-63-7 | >480 | >480 | >480 | 6 | <0.02 | 0.02 | No degradation |
| aniline | L | 62-53-3 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| aviation fuel | L | - | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| benzene | L | 71-43-2 | 28 | 35 | 58 | 2 | 3.0 | 0.05 | No degradation |
| benzonitrile | L | 100-47-0 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| benzoyl chloride | L | 98-88-4 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| benzyl alcohol | L | 100-51-6 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| benzyl chloride | L | 100-44-7 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| bromine | L | 7726-95-6 | imm | 7 | 8 | 0 | high | 0.001 | Discolouration |
| butadiene 1,3 | G | 106-99-0 | >480 | >480 | >480 | 6 | <0.02 | 0.02 | No degradation |
| butane | G | 106-97-8 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| butanol n- | L | 71-36-3 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| Butyl aldehyde | L | 123-72-8 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| Butyl ether n- | L | 142-96-1 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| carbon disulphide | L | 75-15-0 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| chlorine | G | 7782-50-5 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| chloroacetic acid (68%) | L | 79-11-8 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| chlorobenzene | L | 108-90-7 | 120 | 145 | 291 | 5 | 1.5 (max) | 0.05 | No degradation |
| chloroethanol 2- | L | 107-07-3 | >480 | >480 | >480 | 6 | <0.02 | 0.02 | No degradation |
| chloroform | L | 67-66-3 | 3 | 6 | 9 | 0 | 22.5 | 0.01 | No degradation |
| cresol m- | L | 108-39-4 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| cyclohexane | L | 110-82-7 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| cyclohexanone | L | 108-94-1 | 7 | 13 | >480 | 6 | 0.23 | 0.05 | No degradation |
| dichlorodimethylsilane | L | 75-78-5 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | Slight blistering |
| dichloromethane | L | 75-09-2 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| diesel fuel | L | - | >480 | >480 | >480 | 6 | <0.10 | 0.10 | No degradation |
| diethylamine | L | 109-89-7 | 7 | 8 | 11 | 1 | 2.1 | 0.05 | Slight swelling |
| di(2-ethylhexyl)phthalate | L | 117-81-7 | nt | nt | >480 | 6 | nm | 1.0 | No degradation |
| dimethylacetamide N,N | L | 127-19-5 | 223 | >480 | >480 | 6 | 0.08 | 0.05 | No degradation |
| dimethylformamide N,N | L | 68-12-2 | >480 | >480 | >480 | 6 | <0.01 | 0.01 | No degradation |
| dimethyl sulphate | L | 77-78-1 | >480 | >480 | >480 | 6 | <0.02 | 0.02 | No degradation |
| dimethyl sulphide | L | 75-18-3 | 7 | 12 | 29 | 1 | 2.6 | 0.05 | No degradation |
| dimethyl sulfoxide | L | 67-68-5 | >480 | >480 | >480 | 6 | <0.02 | 0.02 | No degradation |
| dioxane 1,4- | L | 123-91-1 | 26 | >480 | >480 | 6 | 0.05 | 0.01 | No degradation |

| Chemical Name | State | CAS Number | Actual (min.) | ASTM (min.) | EN374-3 (min.) | EN Class | SSPR µg/(min.cm²) | MDPR µg/(min.cm²) | Observation |
|--------------------------------------|-------|------------|---------------|-------------|----------------|----------|-------------------|-------------------|--------------------------|
| epichlorohydrin | L | 106-89-8 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| ethanol | L | 64-17-5 | >480 | >480 | >480 | 6 | <0.02 | 0.02 | No degradation |
| ethanolamine | L | 141-43-5 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| ethyl acetate | L | 141-78-6 | >480 | >480 | >480 | 6 | <0.01 | 0.01 | No degradation |
| ethyl cellosolve acetate | L | 111-15-9 | >480 | >480 | >480 | 6 | <0.01 | 0.01 | No degradation |
| ethylene diamine | L | 107-15-3 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| ethylene dibromide | L | 106-93-4 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| ethylene glycol | L | 107-21-1 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| ethylene oxide | G | 75-21-8 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| formaldehyde (37%) | L | 50-00-0 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| formic acid (96%) | L | 64-18-6 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | Discolouration |
| furaldehyde 2- | L | 98-01-1 | 7 | 16 | >480 | 6 | 0.50 | 0.02 | No degradation |
| glutaraldehyde (5%) | L | 111-30-8 | >480 | >480 | >480 | 6 | <0.10 | 0.10 | No degradation |
| heptane | L | 142-82-5 | >480 | >480 | >480 | 6 | <0.02 | 0.02 | No degradation |
| hexane | L | 110-54-3 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| hydrazine monohydrate | L | 7803-57-8 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| hydrochloric acid (37%) | L | 7647-01-0 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| hydrofluoric acid (48%) | L | 7664-39-3 | >480 | >480 | >480 | 6 | <0.02 | 0.02 | No degradation |
| hydrofluoric acid (73%) | L | 7664-39-3 | 30 | 267 | >480 | 6 | 0.18 | 0.01 | No degradation |
| hydrogen chloride | G | 7647-01-0 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| hydrogen fluoride (anhydrous gas) | G | 7664-39-3 | 132 | 244 | 304 | 5 | nm | 0.01 | Degraded and discoloured |
| hydrogen fluoride (anhydrous liquid) | L | 7664-39-3 | 52 | 125 | 228 | 4 | 1.5 | 0.01 | Degraded and discoloured |
| hydrogen peroxide (30%) | L | 7722-84-1 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| kerosene | L | 8008-20-8 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| mercuric chloride (sat. solution) | L | 7487-94-7 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| methacrylic acid | L | 79-41-4 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| methanol | L | 67-56-1 | 46 | 57 | >480 | 6 | 0.54 | 0.02 | No degradation |
| methyl acrylate | L | 96-33-3 | 118 | 231 | >480 | 6 | 0.15 | 0.02 | No degradation |
| methyl-t-Butyl-ether | L | 1634-04-4 | 145 | 248 | >480 | 6 | 0.16 | 0.05 | No degradation |
| methyl chloride | G | 74-87-3 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| methyl ethyl ketone | L | 78-93-3 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| methyl mercaptan | G | 74-93-1 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| methyl methacrylate | L | 80-62-6 | 58 | 97 | >480 | 6 | 0.42 | 0.02 | No degradation |
| methyl vinyl ketone | L | 78-94-4 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| Methyl -2-pyrrolidone n- | L | 872-50-4 | 6 | 12 | >480 | 6 | 0.74 | 0.05 | No degradation |
| methylene bromide | L | 74-95-3 | 28 | 39 | >480 | 6 | 0.45 | 0.05 | No degradation |
| nicotine | L | 54-11-5 | nt | nt | >480 | 6 | nm | 0.10 | No degradation |
| nitric acid (70%) | L | 7697-37-2 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| nitric acid (>90% fuming) | L | 7697-37-2 | >480 | >480 | >480 | 6 | <0.01 | 0.01 | Discolouration |
| nitrobenzene | L | 98-95-3 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| nitromethane (96%) | L | 75-52-5 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| oleum (15% free SO3) | L | 8014-95-7 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| perchloric acid | L | 7601-90-3 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| petrol, leaded | L | - | >480 | >480 | >480 | 6 | <0.10 | 0.10 | No degradation |
| petrol, unleaded | L | 8006-61-9 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| phenol (85%) | L | 108-95-2 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| phosphoric acid (85%) | L | 7664-38-2 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| phosphorus oxytrichloride | L | 10025-87-3 | 373 | 437 | 440 | 5 | 5.7 (max) | 0.001 | No degradation |
| potassium chromate (sat. solution) | L | 7789-00-6 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| propan-2-ol | L | 67-63-0 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| propylene oxide 1,2- | L | 75-56-9 | 75 | 91 | >480 | 6 | 0.55 (max) | 0.05 | No degradation |
| pyridine | L | 110-86-1 | 19 | 22 | >480 | 6 | 0.50 (max) | 0.05 | No degradation |
| 'Roundup' weedkiller | L | - | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| sodium cyanide (45%) | L | 143-33-9 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| sodium hydroxide (40%) | L | 1310-73-2 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |

| Chemical Name | State | CAS Number | Actual (min.) | ASTM (min.) | EN374-3 (min.) | EN Class | SSPR µg/cm²/min | MDPR µg/cm²/min | Observation |
|------------------------------------|-------|------------|---------------|-------------|----------------|----------|-----------------|-----------------|----------------|
| sodium hypochlorite (12% chlorine) | L | 7681-52-9 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| styrene | L | 100-42-5 | 157 | 208 | >480 | 6 | 0.51 (max) | 0.05 | No degradation |
| sulphur dioxide | G | 2025884 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| sulphuric acid (50%) | L | 7664-93-9 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| sulphuric acid (95-98%) | L | 7664-93-9 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| tetrachloroethylene | L | 127-18-4 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| tetrahydrofuran | L | 109-99-9 | 23 | 27 | 41 | 2 | 4.1 | 0.05 | No degradation |
| toluene | L | 108-88-3 | 39 | 79 | 173 | 4 | 2.0 | 0.04 | No degradation |
| toluene 2,4-diisocyanate | L | 584-84-9 | >480 | >480 | >480 | 6 | <0.10 | 0.10 | No degradation |
| toluidine o- | L | 95-53-4 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| trichloroacetic acid (80%) | L | 650-51-1 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| trichlorobenzene 1,2,4- | L | 120-82-1 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| trichloroethylene | L | 79-01-6 | 12 | 14 | 21 | 1 | 12.1 | 0.05 | No degradation |
| trifluoroacetic acid | L | 76-05-1 | >480 | >480 | >480 | 6 | <0.001 | 0.001 | No degradation |
| triethylamine | L | 121-44-8 | 59 | 71 | 168 | 4 | 1.7 | 0.05 | No degradation |
| vinyl acetate | L | 108-05-4 | >480 | >480 | >480 | 6 | <0.05 | 0.05 | No degradation |
| xylene (iso-mix) | L | 1330-20-7 | 377 | 399 | >480 | 6 | 0.35 (max) | 0.05 | No degradation |

Key:

| | | | |
|------------------------|--|------------|--|
| State | L-Liquid, G-Gas | > | Larger than |
| CAS Number | Chemical abstracts service registry number | < | Smaller than |
| ASTM (min.) | Normalized breakthrough time at a rate of 0.1 µg per cm² per minute, in minutes. | imm | Immediate (< 10 min) |
| EN374-3 (min.) | Normalized breakthrough time at a rate of 1.0 µg per cm² per minute, in minutes. | nm | Not measured |
| EN Class | Performance classification according to EN 14325 | nt | Not tested |
| SSPR µg/cm²/min | Steady state permeation rate in µg per cm² per minute | max | Maximum Permeation Rate (SSPR not reached) |
| MDPR µg/cm²/min | Minimum detectable permeation rate in µg per cm² per minute | | |

Specifications, configurations and colours are subject to change without notice. PermaSURE® is a registered trademark of Industrial Textiles and Plastics Limited. Respirex™, GTL™, Hazmax™, Chemprotex™ and Kemblok™ are registered trademarks of Respirex International Limited.



RESPIREX™

Living + Breathing Personal Protection

Respirex International Limited, Unit F Kingsfield Business Centre, Philanthropic Road, Redhill, Surrey, RH1 4DP, United Kingdom

🌐: www.respirex.com ☎: +44 (0)1737 778600 📩: info@respirex.co.uk